



## CoolPoly® D5502 Thermally Conductive Liquid Crystalline Polymer (LCP)

CoolPoly D5502 is a thermally conductive injection molding resin based on a liquid crystal polymer matrix. CoolPoly D5502 is electrically insulative. Thermally conductive polymers like CoolPoly D5502 cool faster than standard injection molding grade resins.

### Typical Injection Molding Conditions

Temperature Settings	SI /Metric	English
Rear Zone	330 - 360 °C	630 - 680 °F
Center Zone	340 - 370 °C	640 - 700 °F
Front Zone	345 - 380 °C	650 - 720 °F
Nozzle	350 - 382 °C	660 - 720 °F
Melt	349 - 393 °C	660 - 740 °F
Mold	93 - 177 °C	200 - 350 °F

### Pressure Settings

Injection	35 - 70 MPa	5000 - 10000 psi
Hold	7 - 35 MPa	1000 - 5000 psi
Back	0 - 0.35 MPa	0 - 50 psi

### Injection Settings

Fill	- fast	- fast
Screw	75 - 150 rpm	75 - 150 rpm
cushion	1 - 1.3 cm.	.3 - .5 inch.

### Drying Conditions

Dew Point	-34 °C	-30 °F
Moisture Content	0.01 %	0.01 %
Time & Temperature	2-4hrs@ 180 °C	2-4hrs@ 355 °F

### Additional Information

A low compression screw (less than 3:1) is recommended. The use of a free flowing nozzle is recommended. A free flowing non-return valve with excellent sealing ability is recommended. Reverse taper nozzles are preferred if the diameters are large and cold slugs or drooling occurs. Suckback should be minimum when necessary.

The information contained herein is provide for preliminary evaluation of the product. Due to the nature of differences in machine and tooling design, adjustments to the processing conditions are expected to be necessary to achieve optimal results. CoolPolymers extends no warranties, makes no representations and assumes no responsibility as to the accuracy or suitability of this information or this product for any purchaser's or user's use or for any consequence of its use. Cool Polymers disclaims any warranty of merchantability or warranty of fitness for any particular use. All statements, technical information and responsibility. Users shall determine the suitability of the products for their own intended application.